# ALCOM® PA66 910/1 GF30 PTFE15

### Polyamide 66

### ALBIS PLASTIC GmbH

### Message:

ALCOM® PA66 910/1 GF30 PTFE15 is a Polyamide 66 (Nylon 66) product filled with 30% glass fiber. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of ALCOM® PA66 910/1 GF30 PTFE15 include engineering/industrial parts and automotive.

Characteristics include:

**REACH Compliant** 

**RoHS Compliant** 

Heat Stabilizer

Lubricated

Wear Resistant

General Information				
Filler / Reinforcement	Glass Fiber,30% Filler by Weight			
Additive	Heat Stabilizer			
	PTFE Lubricant (15%)			
Features	Good Wear Resistance			
	Heat Stabilized			
Uses	Automotive Applications			
	Bearings			
	Machine/Mechanical Parts			
Agency Ratings	EC 1907/2006 (REACH)			
RoHS Compliance	RoHS Compliant			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	1.49	g/cm³	ISO 1183	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Modulus	9500	МРа	ISO 527-2	
Tensile Strain (Break)	2.5	%	ISO 527-2	
Flexural Modulus	8500	МРа	ISO 178	
Flexural Stress	215	МРа	ISO 178	
Impact	Nominal Value	Unit	Test Method	
Charpy Notched Impact Strength	9.0	kJ/m²	ISO 179/1eA	
Charpy Unnotched Impact Strength	60	kJ/m²	ISO 179/1eU	
Thermal	Nominal Value	Unit	Test Method	
Heat Deflection Temperature (1.8 MPa,	245	9.6	150.75.274	
Unannealed)	245	°C	ISO 75-2/A	
Vicat Softening Temperature	252	°C	ISO 306/B50	

Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	2.0 to 12	hr
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	80.0 to 120	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

