

Ferro PP NPP00GC01BK

Polypropylene

Ferro Corporation

Message:

Ferro PP NPP00GC01BK is a Polypropylene material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Typical application of Ferro PP NPP00GC01BK: Automotive

General Information			
Appearance	Black		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.918	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.5	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Durometer Hardness (Shore D)	66		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	34.5	MPa	ASTM D638
Tensile Elongation (Break)	40	%	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790
Flexural Strength (Yield)	43.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	43	J/m	ASTM D256
Unnotched Izod Impact (23°C)	960	J/m	ASTM D256
Gardner Impact	2.82	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	104	°C	
1.8 MPa, Unannealed	60.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT