

ALTECH® PA6 A 2015/210 GF15 IM

Polyamide 6
ALBIS PLASTIC GmbH

Message:

ALTECH® PA6 A 2015/210 GF15 IM is a Polyamide 6 (Nylon 6) product filled with 15% glass fiber. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of ALTECH® PA6 A 2015/210 GF15 IM include engineering/industrial parts, electrical/electronic applications, housings and tools.

Characteristics include:

- REACH Compliant
- RoHS Compliant
- Heat Stabilizer
- Impact Modified

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Heat Stabilizer		
	Impact Modifier		
Features	Heat Stabilized		
	Impact Modified		
Uses	Electrical/Electronic Applications		
	Engineering Parts		
	Housings		
	Machine/Mechanical Parts		
	Power/Other Tools		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5000	MPa	ISO 527-2
Tensile Stress (Break)	85.0	MPa	ISO 527-2
Tensile Strain (Break)	5.0	%	ISO 527-2
Flexural Modulus	4400	MPa	ISO 178
Flexural Stress	145	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	16	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	75	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	200	°C	ISO 75-2/A
Vicat Softening Temperature	205	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature			
Circulation Dryer	60.0 to 80.0	°C	
Desiccant Dryer	60.0 to 80.0	°C	
Drying Time			
Circulation Dryer	2.0 to 6.0	hr	
Desiccant Dryer	2.0 to 6.0	hr	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	80.0 to 90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

