

PRL PPX-GP7

Polyphenylene Ether + PS

Polymer Resources Ltd.

Message:

PRL PPX-GP7 is a Polyphenylene Ether + PS (PPE+PS) product. It can be processed by injection molding and is available in North America.

Characteristics include:

RoHS Compliant

Heat Resistant

General Information			
Features	General Purpose		
	High Heat Resistance		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/11.6 kg)	0.10 to 4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	65.5	MPa	
Break, 3.18 mm	63.4	MPa	
Tensile Elongation (Break, 3.18 mm)	25	%	ASTM D638
Flexural Modulus (3.18 mm)	2380	MPa	ASTM D790
Flexural Strength (Break, 3.18 mm)	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	kJ/m²	ISO 179/1
Notched Izod Impact			ASTM D256
-40°C, 3.18 mm	110	J/m	
23°C, 3.18 mm	210	J/m	
Gardner Impact (3.18 mm)	16.9	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	149	°C	
1.8 MPa, Unannealed, 3.18 mm	143	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	

Drying Temperature	104 to 110	°C
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	260 to 304	°C
Middle Temperature	271 to 310	°C
Front Temperature	282 to 316	°C
Processing (Melt) Temp	302 to 316	°C
Mold Temperature	71.1 to 104	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

