

TAROLOX 111 G7

Polyethylene Terephthalate

Taro Plast S.p.A.

Message:

PET glass fiber reinforced 35%, very high temperature resistance, very good chemical resistance, very good mechanical, thermal and electrical properties, very low moisture absorption, very good dimensional stability. Product must be dried before moulding.
Available: all colors, heat stabilized (H), release agent (W).

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Additive	Heat Stabilizer		
	Mold Release		
Features	Good Chemical Resistance		
	Good Dimensional Stability		
	Good Electrical Properties		
	Good Mold Release		
	Heat Stabilized		
	High Heat Resistance		
	Low Moisture Absorption		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.62 to 1.64	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow	0.15 to 0.30	%	
Across Flow	0.40 to 0.70	%	
Water Absorption (23°C, 24 hr)	0.050	%	ASTM D570, ISO 62
Granule Humidity	< 0.030	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13000	MPa	ASTM D638, ISO 527-2
Tensile Strength (Break)	145	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	2.2	%	ASTM D638, ISO 527-2
Flexural Modulus	10500	MPa	ASTM D790, ISO 178
Flexural Stress			
--	245	MPa	ISO 178
Break	245	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹ (23°C)	10	kJ/m ²	ASTM D256, ISO 179

Charpy Unnotched Impact Strength ² (23°C)	50	kJ/m ²	ASTM D256, ISO 179
Notched Izod Impact (23°C, 3.20 mm)	90	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	225	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	240	°C	ISO 306/B50, ASTM D1525 3
Ball Pressure Test (245°C)	Pass		USI 182-2
Melting Temperature	256	°C	ASTM D211, ISO 121
CLTE - Flow (-30 to 30°C)	3.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (1.00 mm)	34	kV/mm	ASTM D149
Comparative Tracking Index (Solution A)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.970 mm	HB		
1.60 mm	HB		
Glow Wire Ignition Temperature (2.00 mm)	750	°C	IEC 60695-2-13
Oxygen Index	24	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	110 to 130	°C	
Processing (Melt) Temp	270 to 300	°C	
Mold Temperature	90.0 to 130	°C	
Injection Rate	Moderate-Fast		
NOTE			
1.	6x4x50 mm		
2.	6x4x50 mm		
3.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT