

ROPOTEN® K-12-208-61

Low Density Polyethylene

LUKOIL Bulgaria Ltd.

Message:

For insulation and coating of cables.

General Information			
Uses	Cable Jacketing		
	Insulation		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.1 kg)	0.25 to 0.50	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 15.0	MPa	ASTM D638
Tensile Elongation (Break)	> 550	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	> 90.0	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

