

Axiall PVC 10756

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

General purpose, non-lead stabilized jacketing compound recommended for a maximum service temperature or 80 C.

General Information			
Features	General Purpose		
Uses	Cable Jacketing		
	General Purpose		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	17.2	MPa	ASTM D638
Tensile Elongation (Break)	300	%	ASTM D638
Extrusion	Nominal Value	Unit	
Melt Temperature	177	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT