

# Geon™ 130 Series 138

Polyvinyl Chloride Copolymer

Mexichem Specialty Resins, Inc.

## Message:

Geon® 138 is a vinyl ester copolymer dispersion resin, exhibiting fast fusion at low processing temperatures, resulting in energy savings and the ability to work with heat sensitive substrates. The vinyl ester copolymers exhibit stable Brookfield Viscosity aging characteristics. It provides mechanically and chemically foamable properties.

Geon® 138 is recommended for applications where low processing temperatures are required such as carpet tile and walk off mat backings, plastisol inks, general low temperature processing applications, and automotive sealants.

General Information			
Features	Fast Fusion		
	Low VOC		
Uses	Carpet backing		
	Sealant		
	Application in Automobile Field		
Forms	Powder 1		
Processing Method	Slush Molding		
	rotomolding		
	Casting		
	Impregnation coating method		
Physical	Nominal Value	Unit	Test Method
Specific gravity-Calculated value	1.40		ASTM D792
Intrinsic Viscosity	1.2		ASTM D1243-60-A
Humidity-Karl Fisher <sup>1</sup>	0.050	%	Internal method
Volume density	465	g/l	
Relative Viscosity <sup>2</sup>	2.67		Internal method
Optimal stretch-FF <sup>3</sup>	21.0	MPa	ASTM D638
Gloss-60 degree fused 5 mins @ 350F <sup>4</sup>	89	%	Internal method
Transparency-light transmittance <sup>5</sup>	94	%	Internal method
Brokfield Viscosity			
Initial Viscosity @ 2 rpm <sup>6</sup>	4.33	Pa · s	Internal method
Initial Viscosity @ 20 rpm <sup>7</sup>	4.43	Pa · s	Internal method
One Day Viscosity @ 2 rpm <sup>8</sup>	6.18	Pa · s	Internal method
One Day Viscosity @ 20 rpm <sup>9</sup>	6.30	Pa · s	
Cut off the outflow-95 spi <sup>10</sup>	48.00	g/10 min	Internal method
Copolymer Content <sup>11</sup>	4.8	%	Internal method
North fineness <sup>12</sup>	4.75	Hegman	Internal method

Residual Vinyl Chloride Monomer <sup>13</sup>		ppm	Internal method
Methanol extractable <sup>14</sup>	2.2	%	Internal method
polymerization process	Dispersion		
Gel temperature <sup>15</sup>	64	°C	Internal method
K-Value <sup>16</sup>	75.0		Internal method
Additional Information	Nominal Value	Unit	Test Method

Note: The value set forth represents "typical" values and Mexichem Specialty Resins, therefore, makes no representation that the material in any particular shipment will conform to the listed properties. Packaging: This resin is shipped in multi-wall paper bags, net weight 50 lbs, 2500 lbs per pallet. Information shown on the package includes commercial identification number, lot and weight. Geon® ALTC and ASTM D638 (formulation): 100phr Geon® 138, 57phr DINP, 3phr ESO, and 2phr Therm-Chek SP 120 LOHF Geon® STP 390 (formulation): 100phr Geon® 138, and 60phr DOP

NOTE	
1.	Karl Fisher-Geon® 683c
2.	Interrelationship
3.	With provided formulation
4.	60°, FF, ALTC-65
5.	FF, ATLC-66
6.	Initial, V12, Geon® 1010
7.	One day, V12, Geon® 1010
8.	Geon® ALTC 22 (with provided formulation)
9.	Geon® ALTC 22 (with provided formulation)
10.	95 psi, Geon® 1010
11.	Geon® STP PT-LA-026
12.	Geon® 390
13.	Geon® STP 1005
14.	Geon® 894
15.	FF, ALTC-29
16.	Interrelationship

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT