

POLYblend PC/ABS 65H

Polycarbonate + ABS

Polykemi AB

Message:

PC/ABS-blend

General Information			
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	23	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.50 to 0.70	%	
Flow	0.50 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	61.0	MPa	ISO 527-2
Tensile Strain (Yield)	8.0	%	ISO 527-2
Flexural Modulus (23°C)	2500	MPa	ISO 178
Flexural Stress	96.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	17	kJ/m ²	
23°C	48	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹			
0.45 MPa, Unannealed	121	°C	ISO 75-2/B
0.45 MPa, Annealed	123	°C	ISO 75-2/B
1.8 MPa, Unannealed	102	°C	ISO 75-2/A
1.8 MPa, Annealed	107	°C	ISO 75-2/A
Vicat Softening Temperature			
--	134	°C	ISO 306/A50
--	120	°C	ISO 306/B50
Ball Pressure Test (110°C)	Pass		IEC 60695-10-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Ignition Temperature (2.00 mm)	650	°C	IEC 60695-2-13
NOTE			
1.	120°C/hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

