

Durethan® BKV 55 TPX 900116

Polyamide 6

LANXESS GmbH

Message:

PA 6, 55 % glass fibers, injection molding, improved flowability, heat-aging stabilized

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 55% filler by weight		
Additive		heat stabilizer		
Features		Good liquidity		
		Thermal Stability		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.62	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.50	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.10	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.20	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.10	--	%	ISO 2577
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	17300	10500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	215	140	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.5	3.5	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	16500	11000	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	--	210	MPa	ISO 178/A
23°C ⁶	330	210	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	3.0	3.5	%	ISO 178/A
ISO Shortname	PA6, GHR, 10-190, GF55		--	ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	90	85	kJ/m ²	ISO 179/1eU

Notched Izod Impact				ISO 180/1A
-30°C	15	20	kJ/m²	ISO 180/1A
23°C	15	20	kJ/m²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)				
90		85	kJ/m²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	218	--	°C	ISO 75-2/B
1.8 MPa, not annealed	208	--	°C	ISO 75-2/A
Melting Temperature ⁸	221	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	1.2E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	--	cm/cm/°C	ISO 11359-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer				
	80.0		°C	
Drying Time - Dry Air Dryer			hr	
Processing (Melt) Temp			°C	
Mold Temperature			°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT