

Panlite® B-4130R

Polycarbonate

TEIJIN LIMITED

Message:

Carbon fiber reinforced grades-30% Carbon fiber, Flame resistant grade, Non-bromine/non phosphor type

General Information			
UL YellowCard	E50075-241730	E244324-101516632	
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight		
Features	Bromine Free		
	Good Creep Resistance		
	High Rigidity		
Uses	Industrial Applications		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.30 to 0.50	%	
Flow : 4.00 mm	0.010 to 0.15	%	
Water Absorption (23°C, 24 hr)	0.12	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	18200	MPa	ISO 527-2/1
Tensile Stress (Break)	130	MPa	ISO 527-2/5
Tensile Strain (Break)	1.0	%	ISO 527-2/5
Flexural Modulus ¹	16000	MPa	ISO 178
Flexural Stress ²	195	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	8.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	24	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	149	°C	ISO 75-2/B
1.8 MPa, Unannealed	147	°C	ISO 75-2/A
Vicat Softening Temperature	152	°C	ISO 306/B50
CLTE			ISO 11359-2
Flow	1.0E-5	cm/cm/°C	
Transverse	5.0E-5	cm/cm/°C	

RTI Elec (1.50 mm)	80.0	°C	UL 746
RTI Imp (1.50 mm)	80.0	°C	UL 746
RTI Str (1.50 mm)	80.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0 to 10	ohms	IEC 60093
Volume Resistivity	1.0 to 1.0E+2	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-2		UL 94
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

