Hifax TYC 1123P E G14008

Polypropylene Impact Copolymer

LyondellBasell Industries

Message:

Hifax TYC 1123P E is a new high melt flow, low density, mineral filled polypropylene copolymer for injection moulding. It combines a very high flowability, low density, and good esthetics with an excellent impact/stiffness balance and very low CLTE. The grade is UV stabilised and has been specifically designed for moulding of large complex visible parts that require high impact strength as well as good stiffness. This grade is available in custom colour, pellet form.

General Information			
Filler / Reinforcement	Mineral		
Additive	UV Stabilizer		
Features	Good Dimensional Stability		
	Good Processability		
	Good Stiffness		
	Good UV Resistance		
	High Flow		
	High Impact Resistance		
	Impact Copolymer		
	Low Density		
	Non-Smooth Surface Finish		
	Scratch Resistant		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.00	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	31	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	17.4	MPa	ISO 527-2
Flexural Modulus (23°C)	1550	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	5.5	kJ/m²	
23°C	40	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	50.0	°C	ISO 75-2/A
Vicat Softening Temperature	45.0	°C	ISO 306/B50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

