

NORYL™ FE1410PW resin

Polyphenylene Ether + PS

SABIC Innovative Plastics Europe

Message:

NORYL FE1410PW resin is a blend of polyphenylene Oxide (PPO) and polystyrene (PS) resin that contains 10% glass reinforcement. The resin is suitable for injection molding. NORYL FE1410PW resin has been developed for fluid engineering applications that require improved hydrolytic stability. NORYL FE1410PW resin has been certified for potable water applications up to 85C in Europe and North America in limited colors.

General Information			
UL YellowCard	E45329-101521743		
Filler / Reinforcement	Glass Fiber, 10% Filler by Weight		
Features	Hydrolytically Stable		
Uses	Potable Water Applications		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (280°C/10.0 kg)	32.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.20 to 0.40	%	Internal Method
Water Absorption			
Saturation, 23°C	0.20	%	ISO 62
Equilibrium, 50% RH	0.060	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	4780	MPa	ASTM D638
--	4930	MPa	ISO 527-2/1
Tensile Strength			
Break ²	94.0	MPa	ASTM D638
Break	94.0	MPa	ISO 527-2/5
Tensile Elongation			
Break ³	2.8	%	ASTM D638
Break	2.7	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁴	4860	MPa	ASTM D790
-- ⁵	4880	MPa	ISO 178
Flexural Stress			
--	135	MPa	ISO 178
Break, 50.0 mm Span ⁶	135	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179/2C

Charpy Unnotched Impact Strength ⁷			ISO 179/1eU
-30°C	14	kJ/m ²	
23°C	14	kJ/m ²	
Notched Izod Impact			
-30°C	35	J/m	ASTM D256
23°C	35	J/m	ASTM D256
-30°C ⁸	4.0	kJ/m ²	ISO 180/1A
23°C ⁹	4.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
-30°C	230	J/m	ASTM D4812
23°C	230	J/m	ASTM D4812
-30°C ¹⁰	13	kJ/m ²	ISO 180/1U
23°C ¹¹	13	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 100 mm Span ¹²	135	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 3.20 mm	127	°C	ASTM D648
1.8 MPa, Unannealed, 100 mm Span ¹³	126	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	146	°C	ISO 306/A50
--	140	°C	ISO 306/B120
CLTE			ISO 11359-2
Flow : -40 to 40°C	3.0E-5	cm/cm/°C	
Transverse : -40 to 40°C	7.0E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	250 to 270	°C	
Middle Temperature	270 to 290	°C	
Front Temperature	290 to 310	°C	
Nozzle Temperature	280 to 300	°C	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	80.0 to 120	°C	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	1.3 mm/min		
5.	2.0 mm/min		
6.	1.3 mm/min		

7.	80*10*4 sp=62mm
8.	80*10*4
9.	80*10*4
10.	80*10*4
11.	80*10*4
12.	120*10*4 mm
13.	120*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

