

DURANEX® RH1150 T01

Polybutylene Terephthalate

Polyplastics Co., Ltd.

Message:

Low Noise, Damping, GF 15% reinforced, HB

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Features	Noise reduction		
UL File Number	E213445		
Forms	Particle		
Processing Method	Injection molding		
Part Marking Code (ISO 11469)	>PBT-I-GF15		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm ³	ISO 1183
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	81.0	MPa	ISO 527-2
Tensile Strain (Break)	3.2	%	ISO 527-2
Flexural Modulus	4380	MPa	ISO 178
Flexural Stress	126	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	7.7	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	203	°C	ISO 75-2/A
Linear thermal expansion coefficient			Internal method
Flow: 23 to 55°C	3.0E-5	cm/cm/°C	Internal method
Lateral: 23 to 55°C	1.2E-4	cm/cm/°C	Internal method
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	3.0 - 5.0	hr	
Processing (Melt) Temp	250 - 270	°C	
Mold Temperature	40.0 - 80.0	°C	
Holding Pressure	60.0 - 100	MPa	
Screw Speed	100 - 150	rpm	
Injection instructions			

Cooling Time: Plasticization time + alpha or time without sticking in mold

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

