

Elastollan® 1170 A

Thermoplastic Polyurethane Elastomer (Polyether)

BASF Polyurethanes GmbH

Message:

Thermoplastic Polyether Polyurethane Elastomers with outstanding hydrolysis resistance, low temperature flexibility and resistance to micro-organisms.
Typical applications
Cable jackets, plugs and terminations, spiral tubing, Films, ski-boot shells, ear tags, technical mouldings like mining screens, railway pads, seals.

General Information			
Features	Hydrolysis Resistant		
	Low Temperature Flexibility		
	Microbe Resistant		
Uses	Cable Jacketing		
	Film		
	Mining Applications		
	Molded Ear Tags		
	Plugs		
	Seals		
	Sporting Goods		
	Tubing		
Processing Method	Blow Molding		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm ³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	71		ISO 7619
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	< 50.0	mm ³	ISO 4649-A
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			DIN 53504
20% Strain	1.30	MPa	
100% Strain	2.00	MPa	
300% Strain	4.80	MPa	
Tensile Stress (Yield)	30.0	MPa	DIN 53504
Tensile Elongation (Break)	850	%	DIN 53504
Tear Strength ¹	44	kN/m	ISO 34-1
Compression Set			ISO 815

23°C, 72 hr	24	%	
70°C, 24 hr	50	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		
Injection	Nominal Value	Unit	
Processing (Melt) Temp	170 to 240	°C	
Mold Temperature	20.0 to 70.0	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	160 to 220	°C	
NOTE			
1.	Method Bb, Angle (Nicked)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT