

# Utomer UT81P85A

Thermoplastic Polyurethane Elastomer (Polyether)

Shanghai Utomer Material Science Co., Ltd.

Message:

Utomer Polyether type TPU which can be applied to Injection, Extrusion and Calendering.  
Molding cycle is short and efficient for Injection production. The stability melt is easy for Extrusion production. Hydrolysis resistance, low temperature performance with a wide processing window.  
Extrusion Blown, Flat Die Cast Film, Injection Tag Wheel and Cable Jacketing

General Information	
Features	Fast Molding Cycle
	High Melt Stability
	Hydrolysis Resistant
Uses	Blown Film
	Cable Jacketing
	Cast Film
Processing Method	Blown Film
	Calendering
	Cast Film
	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	83 to 87		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	25.0	mm <sup>3</sup>	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	7.00	MPa	
300% Strain	17.0	MPa	
Tensile Strength	28.0	MPa	ASTM D412
Tensile Elongation (Break)	550	%	ASTM D412
Tear Strength	0.100	kN/m	ASTM D624
Compression Set			ASTM D395B
23°C, 70 hr	28	%	
70°C, 24 hr	35	%	
Thermal	Nominal Value	Unit	Test Method

Glass Transition Temperature	-50.0	°C	ASTM D3418
Melting Temperature	185 to 200	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

