

LEXAN™ SLX1432 resin

Polycarbonate

SABIC Innovative Plastics

Message:

Medium viscosity PC copolymer with enhanced UV stabilization and added release agent. Available in opaque colors. Typical minimum color tolerance limit is DE CMC < 1.0

General Information			
Additive	demoulding		
Features	Copolymer		
	Good UV resistance		
	Medium viscosity		
RoHS Compliance	RoHS compliance		
Appearance	Opacity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.22	g/cm ³	ASTM D792
--	1.23	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	9.00	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.80	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.30	%	ISO 62
Equilibrium, 23°C, 50% RH	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2520	MPa	ASTM D638
--	2590	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	65.6	MPa	ASTM D638
Yield	65.4	MPa	ISO 527-2/50
Fracture ³	72.6	MPa	ASTM D638
Fracture	71.3	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	6.1	%	ASTM D638
Yield	5.8	%	ISO 527-2/50
Fracture ⁵	130	%	ASTM D638
Fracture	120	%	ISO 527-2/50

Flexural Modulus			
50.0mm span ⁶	2490	MPa	ASTM D790
-- ⁷	2390	MPa	ISO 178
Flexural Stress			
--	99.8	MPa	ISO 178
Yield, 50.0mm span ⁸	105	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	15	kJ/m ²	ISO 179/1eA
23°C	65	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰ (23°C)	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	120	J/m	ASTM D256
23°C	860	J/m	ASTM D256
-30°C ¹¹	10	kJ/m ²	ISO 180/1A
23°C ¹²	65	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹³ (23°C)	No Break		ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	76.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	132	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	120	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁴	118	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	137	°C	ASTM D1525, ISO 306/B50 10 ¹⁵
--	140	°C	ISO 306/B120
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	6.2E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	6.2E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	271 - 293	°C	
Middle Temperature	282 - 304	°C	
Front Temperature	293 - 316	°C	
Nozzle Temperature	288 - 310	°C	
Processing (Melt) Temp	293 - 316	°C	

Mold Temperature	71.1 - 93.3	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm

NOTE		
1.	5.0 mm/min	
2.	Type 1, 50mm/min	
3.	Type 1, 50mm/min	
4.	Type 1, 50mm/min	
5.	Type 1, 50mm/min	
6.	1.3 mm/min	
7.	2.0 mm/min	
8.	1.3 mm/min	
9.	80*10*3 sp=62mm	
10.	80*10*3 sp=62mm	
11.	80*10*3	
12.	80*10*3	
13.	80*10*3	
14.	80*10*4 mm	
15.	标准 B (120°C/h), 载荷2 (50N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

