

PENTAMID AHT GV30 H TF15 natural

Polyamide 46
PENTAC Polymer GmbH

Message:
Normal viscosity, heat stabilised polyamide 4.6, 30% glass fiber reinforced, PTFE modified

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Additive		PTFE lubricant (15%) heat stabilizer		
Features		Thermal Stability Lubrication		
Agency Ratings		EC 1907/2006 (REACH)		
Appearance		Natural color		
Forms		Particle		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.51	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Transverse flow	0.75	--	%	ISO 294-4
Flow	0.55	--	%	ISO 294-4
Water Absorption				ISO 62
Saturated, 23°C	6.2	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.4	--	%	ISO 62
Viscosity Number	140	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	8600	5700	MPa	ISO 527-2/1
Tensile Stress (Break)	150	100	MPa	ISO 527-2/5
Tensile Strain (Break)	3.0	6.0	%	ISO 527-2/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	48	65	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	280	--	°C	ISO 75-2/B

1.8 MPa, not annealed	265	--	°C	ISO 75-2/A
Melting Temperature	285	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Dielectric Strength	32	--	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	3.30	--		IEC 60250
Comparative Tracking Index	300	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (3.2 mm)	HB	--		UL 94
Additional Information	Dry	Conditioned		Test Method
ISO Shortname	PA46, MHRS, 15-090 N, GF30+X15			ISO 1874
Injection	Dry	Unit		
Drying Temperature	90		°C	
Drying Time	4.0		hr	
Suggested Max Moisture	0.070 - 0.15		%	
Suggested Max Regrind	20		%	
Rear Temperature	295 - 320		°C	
Middle Temperature	305 - 330		°C	
Front Temperature	310 - 320		°C	
Processing (Melt) Temp	305 - 325		°C	
Mold Temperature	80 - 120		°C	
Injection Pressure	85.0		MPa	
Screw L/D Ratio	18.0:1.0 to 22.0:1.0			
Screw Compression Ratio	2.2:1.0 to 2.8:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT