

# Makrolon® ET UV112

Polycarbonate

Covestro - Polycarbonates

## Message:

MVR (300 °C/1.2 kg) 13 cm<sup>3</sup>/10 min; high viscosity; Corrugated Sheets; special grade for the coextrusion of Makrolon ET base resins; with anti stick properties for finished sheets; available in color code 551340 only

General Information	
Features	Viscosity, High
Uses	Wave plate
	Sheet
RoHS Compliance	RoHS compliance
Processing Method	Co-extrusion molding
	Sheet extrusion molding

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.20	g/cm <sup>3</sup>	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	13.0	cm <sup>3</sup> /10min	ISO 1133
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	300	°C	
Mold Temperature	80	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

