

# Andur 7003 AP-F

Polyurethane (Polyether, TDI)  
Anderson Development Company

## Message:

Andur 7003AP-F is a polyether (PPG) based liquid, toluene diisocyanate terminated prepolymer. A water-white clear elastomer with a hardness of 70 Shore A is obtained when this prepolymer is cured with Curene 89-LC. Elastomers of lower hardness can be obtained through the use of plasticizers.

General Information			
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm <sup>3</sup>	ASTM D792
Thermoset	Nominal Value	Unit	Test Method
Thermoset Mix Viscosity	ASTM D2393		
21°C	6800	cP	ASTM D2393
70°C	400	cP	ASTM D2393
Additional Information			

NCO: 2.8 to 3.2%Specific Gravity, ASTM D792, 70°F: 1.04 g/mlSpecific Gravity, ASTM D792, 212°F: 1.03 g/ml

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

