

ULTEM™ 2210EPR resin

Polyether Imide

SABIC Innovative Plastics

Message:

20% Glass fiber filled, high flow Polyetherimide (Tg 217C) with internal mold release and enhanced electroplatability. ECO Conforming, UL94 V0 and 5VA listing.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Additive	demoulding		
Features	Comply with ECO		
	Electroplateable		
	High liquidity		
Agency Ratings	EU Eco		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage			Internal method
Flow: 3.20mm	0.50 - 0.70	%	Internal method
Transverse flow: 3.20mm	0.50 - 0.70	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	6890	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	138	MPa	ASTM D638
Fracture	138	MPa	ASTM D638
Tensile Elongation ³			ASTM D638
Yield	3.0	%	ASTM D638
Fracture	3.0	%	ASTM D638
Flexural Modulus			ASTM D790
100mm span ⁴	6890	MPa	ASTM D790
50.0mm span ⁵	6890	MPa	ASTM D790
Flexural Strength			ASTM D790
Yield, 50.0mm span ⁶	207	MPa	ASTM D790
Fracture, 100mm span ⁷	207	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	80	J/m	ASTM D256
Unnotched Izod Impact (23°C)	590	J/m	ASTM D4812
Instrumented Dart Impact (23°C, Total Energy)	14.9	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 3.20mm	211	°C	ASTM D648
0.45 MPa, unannealed, 6.40mm	214	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	206	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	209	°C	ASTM D648
Vicat Softening Temperature	210	°C	ASTM D1525 ⁸
Linear thermal expansion coefficient			ASTM E831
Flow: -40 to 40°C	3.6E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	7.2E-5	cm/cm/°C	ASTM E831
RTI Elec	105	°C	UL 746
RTI Imp	105	°C	UL 746
RTI	105	°C	UL 746
Electrical	Nominal Value		Test Method
Arc Resistance ⁹	PLC 6		ASTM D495
Comparative Tracking Index (CTI)	PLC 4		UL 746
High Amp Arc Ignition (HAI)	PLC 3		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3		UL 746
Hot-wire Ignition (HWI)	PLC 1		UL 746
Flammability	Nominal Value		Test Method
Flame Rating (0.406 mm)	V-0		UL 94
NOTE			
1.	5.0 mm/min		
2.	Type 1, 5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	2.6 mm/min		
5.	1.3 mm/min		
6.	1.3 mm/min		
7.	2.6 mm/min		
8.	标准 B (120°C/h), 载荷2 (50N)		
9.	Tungsten electrode		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT