

MACOMASS PP MM-PP TV 20

Polypropylene

MACOMASS Verkaufs AG

Message:

Regranulates are created by mechanically/physically processing sorted thermoplastic polymers. They are broken down, washed, dried, melted and reformed into granulates, which are then called reggranulates.

Regranulates are used in plastics processing companies as a raw material. Depending on the quality and taking into account the desired properties of the product, reggranulates can be used by themselves or in combination with new goods.

General Information		
Filler / Reinforcement	Talc filler, 20% filler by weight	
Recycled Content	Yes	
Forms	Particles, after reprocessing	
Physical	Nominal Value	Unit
Density	1.05 - 1.09	g/cm ³
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0 - 12	g/10 min
Mechanical	Nominal Value	Unit
Tensile Stress	> 18.0	MPa
Tensile Strain (Break)	> 15	%
Impact	Nominal Value	Unit
Charpy Unnotched Impact Strength (23°C)	> 35	kJ/m ²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

