

Globalene® ST868K

Polypropylene Random Copolymer
Lee Chang Yung Chemical Industry Corp.

Message:

Globalene® ST868K is a Polypropylene Random Copolymer (PP Random Copolymer) material. It is available in Asia Pacific or North America for injection molding or injection stretch blow molding.

Important attributes of Globalene® ST868K are:

Clarity
Copolymer
Impact Resistant

Typical applications include:

Appliances
Bottles
Containers

General Information	
UL YellowCard	E85783-101834052
Features	High Clarity
	Low Temperature Impact Resistance
	Random Copolymer
Uses	Appliances
	Bottles
	Containers
Forms	Pellets
Processing Method	Injection Molding
	Injection Stretch Blow Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.896	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.4	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	86		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	29.4	MPa	ASTM D638
Tensile Elongation (Yield)	13	%	ASTM D638
Flexural Modulus	1080	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	44	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

