

Perlast® G70A

Perfluoroelastomer

Precision Polymer Engineering Ltd.

Message:

Perlast® G70A uses a unique molecular cross-linking technology to offer the broadest range of chemical resistance of any FFKM with the ability to operate up to a maximum temperature of 260°C (500°F).
An extremely versatile material, Perlast® G70A is suitable for 90% of sealing applications encountered in the chemical processing and refining industries, providing excellent resistance to highly aggressive acids, amines, chlorine and solvent-based chemistries.
Perlast® G70A is available as fully moulded O-rings (any size up to 2m/6.5ft internal diameter), custom shapes and profiles.

- Key Attributes
- Ultimate chemical resistance to a wide range of chemicals
 - Exceptional acid and amine resistance
 - Excellent steam resistance
 - Superior mechanical properties
 - High sealing efficiency
- Typical Applications
- Pumps
 - Valves
 - Mechanical seals
 - Compressors (high H2S concentration environments)
 - Pressure vessels
 - Diesel engines (pre-chambers and exhaust systems)
 - Couplings & Fittings
 - Custom shapes and profiles

General Information			
Features	Solvent resistance		
	Good chemical resistance		
	acid resistance		
	Steam resistance		
Uses	Pump parts		
	Valve/valve components		
	High temperature application		
	Machine/mechanical parts		
	Seals		
	Accessories		
Appearance	Black		
Forms	Customizable form factor		
	Profile		
Hardness	Nominal Value		Test Method
IRHD Hardness	70		ASTM D1415, ISO 48
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	13.2	MPa	ASTM D412, ISO 37

Tensile Strength (Yield)	18.1	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	140	%	ASTM D412, ISO 37
Compression Set (200°C, 24 hr)	10	%	ASTM D395, ISO 815
Thermal	Nominal Value	Unit	
Maximum Operating Temperature	260	°C	
Additional Information			

Minimum Operating Temperature: -15°C (+5°F)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

