

SCHULAKETON MV

Polyketone, Aliphatic

A. Schulman Europe

Message:

Medium viscosity aliphatic Polyketon

General Information			
Processing Method	Extrusion		
	Injection molding		
Resin ID (ISO 1043)	PK		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (240°C/2.16 kg)	6.00	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1400	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	60.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	20	%	ISO 527-2/1A/50
Flexural Modulus ¹	1500	MPa	ISO 178
Flexural Stress ²			ISO 178
3.5% strain	60.0	MPa	ISO 178
9.0% strain	60.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°C	5.0	kJ/m ²	ISO 179/1eA
23°C	22	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			
-40°C	No Break		ISO 179
23°C	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	100	°C	ISO 75-2/Af
Vicat Softening Temperature	191	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Burning Rate (2.00 mm)	< 100	mm/min	ISO 3795
Flame Rating			UL 94, IEC 60695-11-10, -20
1.60 mm	HB		UL 94, IEC 60695-11-10, -20
3.20 mm	HB		UL 94, IEC 60695-11-10, -20

Glow Wire Flammability Index			IEC 60695-2-12
1.50 mm	700	°C	IEC 60695-2-12
3.00 mm	700	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
1.50 mm	725	°C	IEC 60695-2-13
3.00 mm	725	°C	IEC 60695-2-13

Additional Information

1.)
Not for use in food contact applications2.)
Not for use in medical or pharmaceutical applications

NOTE

- | | |
|----|------------|
| 1. | 2.0 mm/min |
| 2. | 2.0 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

