

DuPure® TT 79 V

Polypropylene Impact Copolymer

Ducor Petrochemicals BV

Message:

Description
DuPure TT 79 V is a controlled rheology modified heterophasic high impact polypropylene copolymer. The product shows an excellent fluidity combined with an advanced nucleation system, resulting in fast cycle-times and a high dimensional stability.

Applications
DuPure TT 79 V is suitable for: thin-walled packaging, buckets, housewares.

General Information			
Additive	Nucleating Agent		
Features	Controlled Rheology		
	Fast Molding Cycle		
	Food Contact Acceptable		
	Good Dimensional Stability		
	Good Flow		
	High Impact Resistance		
	Impact Copolymer		
	Nucleated		
Uses	Household Goods		
	Thin-walled Packaging		
Agency Ratings	EC 1907/2006 (REACH)		
	EC 1935/2004		
	EN 71-3		
	EU 10/2011		
	EU 2000/53/EC		
	EU 2002/96/EC (WEEE)		
	EU 2005/84/EC		
	EU 94/62/EC		
	FDA 21 CFR 177.1520(a) 3 (i)		
	FDA 21 CFR 177.1520(c) 3.1a		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1060	MPa	ISO 527-2/1

Tensile Stress (Yield)	21.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	7.0	%	
Break	> 50	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	6.0	kJ/m ²	
0°C	8.0	kJ/m ²	
23°C	17	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-20°C	160	kJ/m ²	
0°C	190	kJ/m ²	
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A
-20°C	5.0	kJ/m ²	
0°C	8.0	kJ/m ²	
23°C	15	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	85.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	52.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	145	°C	ISO 306/A
--	58.0	°C	ISO 306/B
Melting Temperature (DSC)	165	°C	ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

