

Estane® 58311 TPU

Thermoplastic Polyurethane Elastomer (Polyether)

Lubrizol Advanced Materials, Inc.

Message:

Type: Estane® 58311 is an 85A aromatic Polyether-Based Thermoplastic Polyurethane (TPU).
Features: Very good physical properties, hydrolysis resistance, low temperature performance and abrasion. Wide processing window for extrusion.
Uses: Flat Die/Cast Film Extrusion, Profile Extrusion

General Information	
Features	Aroma
	Workability, good
	Good wear resistance
	Low temperature resistance
	Hydrolysis resistance
Uses	cast film
	Profile
Agency Ratings	FDA 21 CFR 177.1680
	FDA 21 CFR 177.2600
	NSF 61
RoHS Compliance	RoHS compliance
Forms	Particle
Processing Method	Extrusion
	cast film
	Profile extrusion molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	82 - 88		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Set (200% Strain)	14	%	ASTM D412
Tensile Stress			ASTM D412
100% strain, 0.762mm	6.20	MPa	ASTM D412
300% strain, 0.762mm	11.7	MPa	ASTM D412
Tensile Strength (Break, 0.762 mm)	45.5	MPa	ASTM D412
Tensile Elongation (Break, 0.762 mm)	520	%	ASTM D412
Tear Strength			
0.762 mm ¹	68.6	kN/m	ASTM D624

Cracking	21	kN/m	ASTM D470
Aging	Nominal Value	Unit	Test Method
Change in Volume (23°C, 24 hr, in water)	1.3	%	ASTM D471
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-49.0	°C	DSC
Melting Temperature	135	°C	DSC
Extrusion	Nominal Value	Unit	
Drying Temperature	104	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Cylinder Zone 1 Temp.	171	°C	
Cylinder Zone 2 Temp.	177	°C	
Cylinder Zone 3 Temp.	182	°C	
Cylinder Zone 4 Temp.	188	°C	
Adapter Temperature	188	°C	
Melt Temperature	185	°C	
Die Temperature	188	°C	
Extrusion instructions			
Dew Point: -40°C Screen Pack Recommendation: 20/40/80/20			
NOTE			
1.	C mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT