# HiFill FR® PA4/6 GF15 FR HS L

## Polyamide 46

## **Techmer Engineered Solutions**

#### Message:

HiFill FR® PA4/6 GF15 FR HS L is a Polyamide 46 (Nylon 46) product filled with 15% glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

Flame Rated

Flame Retardant

Heat Stabilizer

Lubricated

General Information						
Filler / Reinforcement		Glass Fiber,15% Filler by Weight				
Additive		Heat Stabilizer				
		Lubricant				
Features		Flame Retardant				
		Heat Stabilized				
		Lubricated				
Appearance		Colors Available				
Forms		Pellets				
Processing Method		Injection Molding				
Physical	Dry	Conditioned	Unit	Test Method		
Specific Gravity	1.47		g/cm³	ASTM D792		
Molding Shrinkage - Flow (3.18 mm)	0.80		%	ASTM D955		
Water Absorption (24 hr)	2.0		%	ASTM D570		
Mechanical	Dry	Conditioned	Unit	Test Method		
Tensile Strength (Break)	131	82.7	МРа	ASTM D638		
Tensile Elongation (Break)	2.7	5.5	%	ASTM D638		
Flexural Modulus	4830	2960	МРа	ASTM D790		
Flexural Strength	179	110	МРа	ASTM D790		
Impact	Dry	Conditioned	Unit	Test Method		
Notched Izod Impact (23°C, 3.18 mm)	64	96	J/m	ASTM D256		
Thermal	Dry	Conditioned	Unit	Test Method		
Deflection Temperature Under Load (1.8 MPa,						
Unannealed)	290		°C	ASTM D648		
CLTE - Flow	4.0E-5		cm/cm/°C	ASTM D696		
Electrical	Dry	Conditioned	Unit	Test Method		

Volume Resistivity	1.0E+14		ohms·cm	ASTM D257
Dielectric Strength <sup>1</sup>	24		kV/mm	ASTM D149
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.50 mm)	V-0			UL 94
NOTE				

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

