

Grilon® AZ 3/2

Polyamide 66

EMS-GRIVORY

Message:

Grilon® AZ 3/2 is a Polyamide 66 (Nylon 66) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Grilon® AZ 3/2 are:

- Flame Rated
- RoHS Compliant
- Flame Retardant
- Impact Modified
- Wear Resistant

Typical applications include:

- Electrical/Electronic Applications
- Appliances
- Automotive
- Consumer Goods
- Engineering/Industrial Parts

General Information	
Additive	Flame Retardant Impact Modifier
Features	Flame Retardant Good Wear Resistance Impact Modified Low Friction
Uses	Appliance Components Automotive Applications Connectors Consumer Applications Electrical/Electronic Applications Engineering Parts Household Goods Industrial Applications Power/Other Tools Sporting Goods
RoHS Compliance	RoHS Compliant
Forms	Granules
Processing Method	Injection Molding
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1) Secant Modulus vs. Strain (ISO 11403-1)

Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Dry	Conditioned	Unit	Test Method
Density	1.07	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.8	--	%	
Flow	1.6	--	%	
Water Absorption				ISO 62
Saturation, 23°C	8.0	--	%	
Equilibrium, 23°C, 50% RH	2.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	95.0	55.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1700	700	MPa	ISO 527-2
Tensile Stress				ISO 527-2
Yield	45.0	--	MPa	
50% Strain	--	35.0	MPa	
Tensile Strain				ISO 527-2
Yield	5.0	--	%	
Break	--	> 50	%	
Nominal Tensile Strain at Break	> 50	--	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	20	20	kJ/m ²	
23°C	90 kJ/m ²	No Break		
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	170	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	65.0	--	°C	ISO 75-2/A
Continuous Use Temperature				Internal Method
-- ¹	90.0 to 110	--	°C	
-- ²	220	--	°C	
Melting Temperature ³	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.5E-4	--	cm/cm/°C	

Transverse	1.5E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+14	1.0E+13	ohms·cm	IEC 60093
Electric Strength	29	27	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA66-HI, MHR, 14-020 N	--		ISO 1874
NOTE				
1.	Long Term			
2.	Short Term			
3.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

