

HiFill® MD PA66 0125 LE

Polyamide 66
Techmer Engineered Solutions

Message:
Nylon PA 66, Metallic Filler, Activated for Metal Detection, Low Extractables for FDA Compliant Applications

General Information			
Features	Low Extractables		
	Metal Detectable		
Agency Ratings	FDA Unspecified Rating		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.7	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	72.4	MPa	ASTM D638
Tensile Elongation (Yield)	8.0	%	ASTM D638
Flexural Modulus	2760	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Annealed	138	°C	
1.8 MPa, Unannealed	82.2	°C	
Injection	Nominal Value	Unit	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	282 to 293	°C	
Middle Temperature	288 to 299	°C	
Front Temperature	277 to 288	°C	
Nozzle Temperature	282 to 293	°C	
Processing (Melt) Temp	282 to 304	°C	
Mold Temperature	54.4 to 93.3	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

