HANWHA 8600L

Low Density Polyethylene

Hanwha Chemical

Message:

CLNA-8600L is a low density polyethylene(LDPE) compound designed for the insulation of coaxial cable and radio frequency communication cables. It has excellent electrical properties. CLNA-8600L is commonly used by blending with CHNA-8600H prior to extrusion. Recommended blend ratios of 8600H/8600L/Nucleating agent are 68~78 / 30~20 / 2 %.

Applications:

8600H&L can be used coaxial cable and radio frequency(RF) communication cables using a gas injection foaming process.

| General Information | | | |
|---------------------------------------|---------------------------------|----------|-------------|
| Features | Foamable | | |
| | Good Electrical Properties | | |
| | Low Density | | |
| | | | |
| Uses | Blending | | |
| | Communication Wire Insulation | | |
| | Wire & Cable Applications | | |
| | | | |
| Agency Ratings | ASTM D 1248, I, Class A, Cat. 3 | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| | Foam Processing | | |
| | Gas-Assisted Injection Molding | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.921 | g/cm³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 | | | |
| kg) | 2.0 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 11.8 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 600 | % | ASTM D638 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | < -76.0 | °C | ASTM D746 |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity | > 1.0E+16 | ohms·cm | ASTM D257 |
| Dielectric Constant (1 MHz) | 2.28 | | ASTM D150 |
| Dissipation Factor (1 MHz) | 8.0E-5 | | ASTM D150 |
| Extrusion | Nominal Value | Unit | |
| Melt Temperature | 160 to 200 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

