

Durethan® BKV 30 H3.0 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 30 % glass fibers, injection molding, heat-aging stabilized

General Information				
UL YellowCard		E245249-473587	E245249-473590	
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
Processing Method		Injection Molding		
Multi-Point Data		Creep Modulus vs. Time (ISO 11403-1)		
		Isochronous Stress vs. Strain (ISO 11403-1)		
		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
		Shear Modulus vs. Temperature (ISO 11403-1)		
		Specific Volume vs Temperature (ISO 11403-2)		
		Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.36	--	g/cm³	ISO 1183
Apparent Density	0.70	--	g/cm³	ISO 60
Molding Shrinkage				ISO 2577
Across Flow : 280°C, 2.00 mm ¹	0.69	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.12	--	%	
Flow : 280°C, 2.00 mm ³	0.24	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.070	--	%	
Water Absorption				ISO 62
Saturation, 23°C	7.0	--	%	
Equilibrium, 23°C, 50% RH	2.1	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	210	100	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9800	6100	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	180	105	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	6.0	%	ISO 527-2/5

Tensile Creep Modulus				ISO 899-1
1 hr	--	5100	MPa	
1000 hr	--	4100	MPa	
Flexural Modulus ⁵ (23°C)	8600	5100	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain, 23°C	--	145	MPa	
23°C ⁶	280	170	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	6.0	%	ISO 178/A
Burning Behavior ⁸	passed	--		ISO 3795
ISO Shortname	PA 6, GHR, 14-100, GF30	--		ISO 1874
Residual Moisture Content	0.030 to 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	10	kJ/m ²	
23°C	15	20	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	70	kJ/m ²	
23°C	80	95	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
-30°C	10	10	kJ/m ²	
23°C	15	20	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	70	80	kJ/m ²	
23°C	75	85	kJ/m ²	
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	6.00	5.00	J	
23°C	8.00	14.0	J	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	215	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	110	--	°C	ISO 75-2/C
Vicat Softening Temperature				
--	200	--	°C	ISO 306/B50
--	> 200	--	°C	ISO 306/B120
Melting Temperature ⁹	222	--	°C	ISO 11357-3
CLTE				ISO 11359-2

Flow : 23 to 55°C	2.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+12	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	40	35	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
23°C, 100 Hz	4.00	15.0		
23°C, 1 MHz	4.00	5.00		
Comparative Tracking Index (Solution A)	525	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
--	HB	--		
1.60 mm	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.800 mm	700	--	°C	
1.60 mm	700	--	°C	
3.00 mm	700	--	°C	
Oxygen Index ¹⁰	22	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	270 to 290		°C	
Mold Temperature	80.0 to 120		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	US-FMVSS302			
9.	10°C/min			
10.	Procedure A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT