

ELASTOSIL® P 7676 A/B

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-2
Orthopedic Products, Pharmaceuticals & Healthcare

General Information	
Features	Biocompatible
	BPA Free
	Breathable
	Good Chemical Resistance
	Good Flexibility
	Good Sterilizability
	Good Thermal Stability
	High Gas Permeability
	High Heat Resistance
	Low to No Odor
	Low to No Water Absorption
	Non-Toxic
	Steam Resistant

Uses	Medical/Healthcare Applications
	Pharmaceuticals
	Prosthetics

Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Pot Life	100	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	< 0		ISO 868
Tensile Strength	0.600	MPa	ISO 37
Tensile Elongation at Break	500	%	ISO 37
Tear Strength	1.00	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

