

EXCELLOY TK30

Acrylonitrile Butadiene Styrene + PBT

Techno Polymer Co, Ltd.

Message:

EXCELLOY TK30 is an Acrylonitrile Butadiene Styrene + PBT (ABS+PBT) product. It can be processed by injection molding and is available in Asia Pacific or North America.

Characteristics include:

Chemical Resistant

High Flow

General Information			
Features	Good Chemical Resistance		
	High Flow		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm³	ISO 1183, ASTM D1505
Melt Mass-Flow Rate (MFR) (240°C/10.0 kg)	50	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	106		ASTM D785
R-Scale	104		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	41.2	MPa	ASTM D638
Yield	41.0	MPa	ISO 527-2
Flexural Modulus			
--	2260	MPa	ASTM D790
--	1830	MPa	ISO 178
Flexural Strength			
--	68.6	MPa	ASTM D790
--	61.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	7.0	kJ/m²	ISO 179
Notched Izod Impact	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	94.0	°C	ASTM D648
0.45 MPa, Unannealed	77.0	°C	ISO 75-2/B
Injection	Nominal Value	Unit	

Drying Temperature	80.0 to 90.0	°C
Drying Time	2.0 to 5.0	hr
Rear Temperature	220 to 270	°C
Middle Temperature	220 to 270	°C
Front Temperature	220 to 270	°C
Mold Temperature	40.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

