

PENTAMID A CV30 H black

Polyamide 66
PENTAC Polymer GmbH

Message:
Normal viscosity, heat stabilised polyamide 66, 30% carbon fiber reinforced

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 30% filler by weight		
Additive	heat stabilizer		
Features	Thermal Stability		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Transverse flow	0.30	%	ISO 294-4
Flow	0.15	%	ISO 294-4
Water Absorption			ISO 62
Saturated, 23°C	5.2	%	ISO 62
Equilibrium, 23°C, 50% RH	1.6	%	ISO 62
Viscosity Number	140	cm ³ /g	ISO 307
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	24200	MPa	ISO 527-2/1
Tensile Stress (Break)	195	MPa	ISO 527-2/5
Tensile Strain (Break)	1.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.2	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	40	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	255	°C	ISO 75-2/B
1.8 MPa, not annealed	250	°C	ISO 75-2/A
Melting Temperature	260	°C	ISO 11357-3
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.6 mm	HB		UL 94
3.2 mm	HB		UL 94
Additional Information	Nominal Value		Test Method

ISO Shortname	PA66, MHRC, 14-220 N, CF30	ISO 1874
Injection	Nominal Value	Unit
Drying Temperature	80	°C
Drying Time	3.0	hr
Suggested Max Moisture	0.050 - 0.13	%
Suggested Max Regrind	20	%
Rear Temperature	265 - 290	°C
Middle Temperature	275 - 300	°C
Front Temperature	280 - 290	°C
Processing (Melt) Temp	270 - 300	°C
Mold Temperature	60 - 100	°C
Injection Pressure	78.0	MPa
Screw L/D Ratio	18.0:1.0 to 22.0:1.0	
Screw Compression Ratio	2.2:1.0 to 2.8:1.0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

