

PENTAMID B GV30 H schwarz

Polyamide 6
PENTAC Polymer GmbH

Message:
normal viscosity, heat stabilised polyamide 6, 30% glass fiber reinforced

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
Uses		Handles		
Agency Ratings		EC 1907/2006 (REACH)		
Appearance		Black		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.70	--	%	
Flow	0.40	--	%	
Water Absorption				ISO 62
Saturation, 23°C	6.5	--	%	
Equilibrium, 23°C, 50% RH	2.1	--	%	
Viscosity Number	145	--	cm ³ /g	ISO 307
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 961/30)	220	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10000	5500	MPa	ISO 527-2/1
Tensile Stress (Break)	180	120	MPa	ISO 527-2
Tensile Strain (Break)	3.7	7.5	%	ISO 527-2
Flexural Modulus	8100	--	MPa	ISO 178
Flexural Stress	240	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	11	--	kJ/m ²	
23°C	13	20	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	--	kJ/m ²	

23°C	90	95	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	215	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	205	--	°C	ISO 75-2/A
Melting Temperature (DSC)	222	--	°C	ISO 1874
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength (1.00 mm)	33	--	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	3.80	--		IEC 60250
Comparative Tracking Index	525	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		
3.20 mm	HB	--		
Additional Information	Dry	Conditioned		Test Method
ISO Type				
--	--	PA6, MHRC, 14-100, GF30		ISO 1874
--	PA6, MHRC, 14-100, GF30	--		ISO 11357
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	3.0		hr	
Suggested Max Moisture	0.090		%	
Suggested Max Regrind	20		%	
Rear Temperature	260 to 285		°C	
Middle Temperature	275 to 290		°C	
Front Temperature	275 to 285		°C	
Processing (Melt) Temp	280		°C	
Mold Temperature	80.0		°C	
Injection Pressure	71.5		MPa	
Holding Pressure	42.9		MPa	
Screw L/D Ratio	20.0:1.0			
Screw Compression Ratio	2.2:1.0 to 2.8:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

