

# TOTAL Polystyrene Compound 260-25

High Impact Polystyrene  
TOTAL Refining & Chemicals

Message:

Polystyrene Compound 260-25 is an easy flow, HB recycled high impact polystyrene for injection molding application.  
It contains 25% of recycled polystyrene.  
It is recommended for the manufacturing of articles which require good dimensional stability.

Applications:

- TV Cover
- Office Automation
- Electrical and Electronic

General Information			
Recycled Content	Yes, 25%		
Features	Good dimensional stability		
	Recyclable materials		
	Good liquidity		
Uses	Electrical/Electronic Applications		
	TV housing		
	Business equipment		
Agency Ratings	EC 1907/2006 (REACH)		
UL File Number	E314268		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02 - 1.04	g/cm <sup>3</sup>	ASTM D792
Apparent Density	0.60	g/cm <sup>3</sup>	ASTM D1895
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	6.0 - 9.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage - Flow	0.40 - 0.70	%	ASTM D955
Water Absorption			
Balance	< 0.10	%	ASTM D570
Equilibrium, 23°C, 50% RH	< 0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C, Injection Molded)	25.0 - 27.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break, 23°C, Injection Molded)	25 - 40	%	ASTM D638, ISO 527-2
Flexural Modulus (23°C, Injection Molded)	1800 - 2200	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C, injection molding	59 - 76	J/m	ASTM D256
23°C, injection molding	6.5 - 8.5	kJ/m <sup>2</sup>	ISO 180

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	85.0 - 95.0	°C	ISO 306/A50, ASTM D1525 1
Heat Distortion			
--	70 - 85	°C	ISO 75-2
--	70 - 85	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	160 - 180	°C	
Middle Temperature	180 - 200	°C	
Front Temperature	190 - 210	°C	
Nozzle Temperature	210 - 230	°C	
Injection instructions			
Zone 4 Temperature: 200 to 220°C			
NOTE			

1. 速率 A (50°C/h), 压力1 (10N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

