

Huaфон JF-PDY-511H

Polyurethane
Huaфон Group Co., Ltd.

Message:
Water-borne PU Resin for Adhesive Layer
Characteristics
Hydrolysis resistance, direct coating adhesive for dry process

General Information		
Features	Aromatic	
	Hydrolysis Resistant	
Uncured Properties	Nominal Value	Unit
Solids Content	34 to 36	%
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	1.00 to 1.40	MPa
Tensile Strength	> 10.0	MPa
Tensile Elongation at Break	> 500	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT