

POLYREX® PG-80

General Purpose Polystyrene

CHI MEI CORPORATION

Message:

POLYREX® PG-80 is a General Purpose Polystyrene product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

RoHS Compliant

General Information			
UL YellowCard	E56070-245768		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/5.0 kg	4.0	g/10 min	
220°C/10.0 kg	11	g/10 min	
Melt Volume-Flow Rate (MVR) (200°C/5.0 kg)	4.00	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785
Ball Indentation Hardness (H 358/30)	144	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			
Yield	47.0	MPa	ISO 527-2/50
Break	45.0	MPa	ISO 527-2/50
3.00 mm ¹	49.0	MPa	ASTM D638
Tensile Elongation			
Break, 3.00 mm ²	2.0	%	ASTM D638
Break	5.0	%	ISO 527-2/50
Flexural Modulus			
6.00 mm ³	5980	MPa	ASTM D790
-- ⁴	2400	MPa	ISO 178
Flexural Strength			
6.00 mm ⁵	67.7	MPa	ASTM D790
-- ⁶	68.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.0	kJ/m ²	ISO 179, ISO 179/2C
Charpy Unnotched Impact Strength			
--	11	kJ/m ²	ISO 179

--	17	kJ/m ²	ISO 179/2U
Notched Izod Impact			
23°C, 3.00 mm	18	J/m	ASTM D256
23°C, 6.00 mm	17	J/m	ASTM D256
--	2.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength	9.0	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed	84.0	°C	ASTM D648
1.8 MPa, Unannealed	80.0	°C	ISO 75-2/A
1.8 MPa, Annealed	94.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature			
--	97.0	°C	ASTM D1525, ISO 306/B120 6 ⁷
--	96.0	°C	ISO 306/A50
--	102	°C	ISO 306/A120
--	94.0	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.59 mm	HB		
1.60 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	160 to 180	°C	
Middle Temperature	190 to 210	°C	
Front Temperature	185 to 205	°C	
Mold Temperature	40.0 to 70.0	°C	
NOTE			
1.	6.0 mm/min		
2.	6.0 mm/min		
3.	2.8 mm/min		
4.	2.0 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		
7.	Rate A (50°C/h)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

