

PIVINEL™ SYR-NT

Polyvinyl Chloride

HELLENIC CABLES S.A.

Message:

Description: PVC based compounds for the textiles plasticizing

Packaging: In PE bags of 25 kg or in big bags of approximately 1000 kg.

Use: Textiles plasticizing, non toxic with UV protection, oilskin etc. ELASTEL 1306-2.

General Information		
Features	Good UV Resistance	
Uses	Textile Applications	
Processing Method	Extrusion	
Physical	Nominal Value	Unit
Specific Gravity	1.22	g/cm ³
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	150	°C
Cylinder Zone 2 Temp.	160	°C
Cylinder Zone 3 Temp.	165	°C
Cylinder Zone 4 Temp.	170	°C
Cylinder Zone 5 Temp.	175	°C
Cylinder Zone 6 Temp.	175	°C
Cylinder Zone 7 Temp.	175	°C
Cylinder Zone 8 Temp.	175	°C
Cylinder Zone 9 Temp.	175	°C
Head Temperature	175	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

