

Anjacom® 100V

Polycarbonate
Almaak International GmbH

Message:

Anjacom® 100V is a Polycarbonate (PC) material. It is available in Europe for injection molding.
Important attributes of Anjacom® 100V are:
Flame Rated
Low Viscosity

General Information			
UL YellowCard	E169818-457844		
Features	Low Viscosity		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.20	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	20.0	cm ³ /10min	ISO 1133
Water Absorption			ISO 62
23°C, 24 hr	0.30	%	
Equilibrium, 23°C, 50% RH	0.15	%	
Relative Viscosity	1.26		ISO 1628
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/1
Tensile Stress (Yield)	63.0	MPa	ISO 527-2/50
Tensile Strain (Break)	6.0	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	137	°C	ISO 75-2/B
1.8 MPa, Unannealed	125	°C	ISO 75-2/A
Glass Transition Temperature	149	°C	DSC
Vicat Softening Temperature	144	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Electric Strength	30	kV/mm	IEC 60243-1
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-2		UL 94
Glow Wire Flammability Index (4.00 mm)	850	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	

Drying Temperature	120	°C
Drying Time	2.0 to 5.0	hr
Suggested Max Moisture	0.020	%
Processing (Melt) Temp	280 to 320	°C
Mold Temperature	80.0 to 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

