

LG PMMA IH830A

Polymethyl Methacrylate Acrylic
LG MMA Corp.

Message:

LG PMMA IH830A is a Polymethyl Methacrylate Acrylic material. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of LG PMMA IH830A are:

Flame Rated

RoHS Compliant

Typical application of LG PMMA IH830A: Automotive

General Information			
Features	General Purpose		
Uses	General Purpose		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.60	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	96		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	63.7	MPa	ASTM D638
Tensile Elongation (Yield)	10	%	ASTM D638
Flexural Modulus	3300	MPa	ASTM D790
Flexural Strength (Yield)	130	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.4	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	15	kJ/m ²	ISO 179/1eU
Notched Izod Impact (Area)	1.50	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	95.0	°C	ASTM D648
Vicat Softening Temperature	108	°C	ASTM D1525 ¹
CLTE - Flow	6.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	ASTM D257
Dielectric Strength ²	20	kV/mm	ASTM D149
Dielectric Constant (60 Hz)	3.10		ASTM D150
Dissipation Factor (60 Hz)	0.050		ASTM D150

Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ASTM D542
Transmittance (3200 μm)	92.0	%	ASTM D1003
Haze (3200 μm)	< 0.10	%	ASTM D1003
NOTE			
1.	Loading 1 (10 N)		
2.	4000 V/sec		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

