

Pier One POM AC GC10 BK

Acetal (POM) Copolymer

Pier One Polymers, Inc.

Message:

Pier One POM AC GC10 BK is an Acetal (POM) Copolymer material filled with 10% glass fiber. It is available in North America for injection molding.
Primary attribute of Pier One POM AC GC10 BK: Copolymer.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Copolymer		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/1.05 kg)	7.0 to 9.0	g/10 min	ASTM D1238
Ash Content	7.0 to 13	%	ASTM D4218
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	67.6	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	9.0	%	ASTM D638
Flexural Modulus (23°C)	4480	MPa	ASTM D790
Flexural Strength (23°C)	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	67	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	149	°C	ASTM D648
Peak Melting Temperature	166	°C	ASTM D3418
Injection	Nominal Value	Unit	
Drying Temperature	82.0	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	182 to 198	°C	
Mold Temperature	82.0 to 93.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

