

Ultramid® Structure A3WG8 LFX BK23215

Polyamide 66

BASF Corporation

Message:

Ultramid Structure A3WG8 LFX BK23215 is a 40% long glass-fiber reinforced and heat aging resistant injection molding grade designed for applications requiring excellent strength and stiffness.

General Information				
Filler / Reinforcement		Long glass fiber, 40% filler by weight		
Features		Rigidity, high		
		High strength		
		Good heat aging resistance		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS compliance		
Appearance		Black		
Forms		Particle		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.47	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Transverse flow	0.66	--	%	ISO 294-4
Flow	0.45	--	%	ISO 294-4
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	13500	10200	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	240	169	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.4	2.4	%	ISO 527-2
Flexural Modulus (23°C)	12400	9300	MPa	ISO 178
Flexural Stress (23°C)	360	268	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-30°C	22	20	kJ/m ²	ISO 179
23°C	21	21	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength				ISO 179
-30°C	68	63	kJ/m ²	ISO 179
23°C	82	82	kJ/m ²	ISO 179
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	260	--	°C	ISO 75-2/A

Melting Temperature (DSC)	260	--	°C	ISO 3146
Injection	Dry	Unit		
Drying Temperature	83		°C	
Drying Time	2.0 - 4.0		hr	
Suggested Max Moisture	0.15		%	
Processing (Melt) Temp	290 - 310		°C	
Mold Temperature	80 - 100		°C	
Injection Pressure	3.50 - 12.5		MPa	
Injection Rate	Fast			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

