

LEXAN™ 925 resin

Polycarbonate

SABIC Innovative Plastics

Message:

LEXAN 925 Polycarbonate (PC) resin is a non-filled, injection moldable grade. This non-chlorinated, non-brominated flame retardant PC has a UL V0 rating. LEXAN resin 925 is available in various opaque color options and is a general-purpose resin that is an excellent candidate for a wide variety of applications.

General Information			
UL YellowCard	E207780-228401		
Additive	Flame retardancy		
Features	Chlorine Free		
	General		
	Bromine-free		
	Flame retardancy		
Uses	General		
Appearance	Opacity		
	Available colors		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	14	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.80	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2280	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	62.1	MPa	ASTM D638
Fracture	65.5	MPa	ASTM D638
Tensile Elongation ³			ASTM D638
Yield	6.0	%	ASTM D638
Fracture	130	%	ASTM D638
Flexural Modulus ⁴ (50.0 mm Span)	2340	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 50.0 mm Span)	101	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	800	J/m	ASTM D256
Instrumented Dart Impact (23°C, Total Energy)	73.4	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, unannealed, 3.20mm	138	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	127	°C	ASTM D648
Vicat Softening Temperature	143	°C	ASTM D1525 ⁶
Linear thermal expansion coefficient			ASTM E831
Flow: -40 to 40°C	6.7E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	6.7E-5	cm/cm/°C	ASTM E831
RTI Elec	130	°C	UL 746
RTI Imp	120	°C	UL 746
RTI	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Arc Resistance ⁷	PLC 7		ASTM D495
Comparative Tracking Index (CTI)	PLC 2		UL 746
High Amp Arc Ignition (HAI)	PLC 3		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 4		UL 746
Hot-wire Ignition (HWI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.10 mm)	V-0		UL 94
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 mm)	875	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	266 - 288	°C	
Middle Temperature	277 - 299	°C	
Front Temperature	288 - 310	°C	
Nozzle Temperature	282 - 304	°C	
Processing (Melt) Temp	288 - 310	°C	
Mold Temperature	71.1 - 93.3	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.025 - 0.076	mm	
NOTE			
1.	50 mm/min		
2.	Type 1, 50mm/min		
3.	Type 1, 50mm/min		
4.	1.3 mm/min		
5.	1.3 mm/min		
6.	标准 B (120°C/h), 载荷2 (50N)		
7.	Tungsten electrode		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

