

TOTAL Polypropylene Aceso® PPM R021 S01

Polypropylene Random Copolymer

TOTAL Refining & Chemicals

Message:

Polypropylene Aceso® PPM R021 S01 is random copolymer polypropylene with a Melt Flow Index of 1.8 g/10 min specially developed for the extrusion blow-moulding of medical containers and medical devices, to the exclusion of implants. This grade can also be injection moulded.
Polypropylene Aceso® PPM R021 S01 is the version of the Polypropylene Aceso® PPM R021 based on a phthalate-free catalyst.

General Information	
Features	Random copolymer
Uses	Container
	Medical/nursing supplies
	Medical devices
Agency Ratings	EC 1907/2006 (REACH)
RoHS Compliance	RoHS compliance
Forms	Particle
Processing Method	Extrusion blow molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	0.902	g/cm ³	ISO 1183
Apparent Density	0.53	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.8	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	82		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1000	MPa	ISO 527-2
Tensile Stress (Yield)	26.0	MPa	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2
Flexural Modulus	900	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179
Notched Izod Impact (23°C)	6.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	130	°C	ISO 306/A50
--	67.0	°C	ISO 306/B50
Melting Temperature (DSC)	149	°C	ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

