

# Mirathane™ E165D

Thermoplastic Polyurethane Elastomer (Polyester)

Miracll Chemicals Co., Ltd.

## Message:

Mirathane™ E165D is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) product. It is available in Asia Pacific. Applications of Mirathane™ E165D include coating applications, engineering/industrial parts, hose/tubing, additive/masterbatch and automotive.

Characteristics include:

- Chemical Resistant
- Good Flexibility
- Puncture Resistant
- Wear Resistant

General Information	
Features	Good Abrasion Resistance
	Kink Resistant
	Low Temperature Flexibility
	Oil Resistant
	Puncture Resistant
	Solvent Resistant
Uses	Automotive Applications
	Belts/Belt Repair
	Coating Applications
	Compounding
	Fabric Coatings
	Film
	Footwear
	Hose
	Overmolding
	Seals
	Sheet
	Tubing
	Wheels
	Wire & Cable Applications

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	65		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	35.0	mm <sup>3</sup>	DIN 53516
Elastomers	Nominal Value	Unit	Test Method

Tensile Stress			ASTM D412
100% Strain	20.0 to 22.0	MPa	
300% Strain	35.0 to 40.0	MPa	
Tensile Strength (Yield)	40.0 to 45.0	MPa	ASTM D412
Tensile Elongation (Break)	300 to 350	%	ASTM D412
Tear Strength	200 to 210	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature <sup>1</sup>	-25.0	°C	ASTM D3417
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT