

CYCOLAC™ MG37EPX resin

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

ABS plating grade optimized for a broad processing window for both painted and plated applications.

General Information			
Features	Electroplateable		
	Sprayable		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	21	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.60	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2760	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/5
Yield	48.5	MPa	ISO 527-2/5
Fracture	39.6	MPa	ISO 527-2/5
Tensile Strain			ISO 527-2/5
Yield	2.1	%	ISO 527-2/5
Fracture	16	%	ISO 527-2/5
Flexural Modulus ¹	2480	MPa	ISO 178
Flexural Stress	73.2	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ²			ISO 180/1A
-40°C	6.2	kJ/m ²	ISO 180/1A
-30°C	8.2	kJ/m ²	ISO 180/1A
23°C	23	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³ (1.8 MPa, Unannealed, 64.0 mm Span)	82.0	°C	ISO 75-2/Af
Vicat Softening Temperature	98.2	°C	ISO 306/B50
Linear thermal expansion coefficient			ISO 11359-2
Flow: -40 to 40°C	6.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	6.0E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	82.2 - 93.3	°C	
Drying Time	2.0 - 4.0	hr	

Drying Time, Maximum	8.0	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	50 - 70	%
Rear Temperature	216 - 229	°C
Middle Temperature	232 - 243	°C
Front Temperature	249 - 268	°C
Nozzle Temperature	254 - 279	°C
Processing (Melt) Temp	254 - 279	°C
Mold Temperature	37.8 - 82.2	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	30 - 60	rpm
Vent Depth	0.038 - 0.051	mm

NOTE

- | | |
|----|------------|
| 1. | 2.0 mm/min |
| 2. | 80*10*4 |
| 3. | 80*10*4 mm |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

