

# Mylar® MO 21 (750 guage)

Polyethylene Terephthalate

DuPont Teijin Films U.S.

Message:

Mylar® MO 21 (750 guage) is a Polyethylene Terephthalate (PET) product. It is available in North America. Applications of Mylar® MO 21 (750 guage) include coating applications, film and wire & cable.

Characteristics include:

Heat Resistant

High Strength

Low Moisture Absorption

General Information			
UL YellowCard	E93687-252918		
Features	Extraction Resistant		
	Good Electrical Properties		
	Good Thermal Stability		
	High Strength		
	Low Moisture Absorption		
Uses	Diaphragms		
	Electronic Insulation		
	Film		
	Laminates		
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm <sup>3</sup>	ASTM D1505
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	190	µm	
Tensile Strength			ASTM D882
MD : Yield	179	MPa	
TD : Yield	200	MPa	
Tensile Elongation			ASTM D882
MD : Break	150	%	
TD : Break	130	%	
Optical	Nominal Value	Unit	Test Method
Haze	40	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

