

ACRYPET® VHM

Polymethyl Methacrylate Acrylic
Lucite International Holland BV

Message:

ACRYPET® VHM is a polymethyl methacrylate-acrylic material. This product is available in Europe.

General Information			
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	3.1	g/10 min	ISO 1133
Spiral Flow			Internal method
-- ¹	14.0	cm	Internal method
-- ²	23.0	cm	Internal method
Molding Shrinkage	0.20 - 0.60	%	Internal method
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	101		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	76.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	5.0	%	ISO 527-2/1A/5
Flexural Modulus	3300	MPa	ISO 178
Flexural Stress	135	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.4	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	20	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	100	°C	ISO 75-2/A
Vicat Softening Temperature	107	°C	ISO 306/B
CLTE - Flow	6.0E-5	cm/cm/°C	ASTM D696
Specific Heat	1500	J/kg/°C	JIS K7123
Thermal Conductivity	0.20	W/m/K	ASTM C177
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ASTM D542
Transmittance (Total, 3000 µm)	93.0	%	ISO 13468
Haze (3000 µm)	0.30	%	ISO 14782
NOTE			
1.	Melt temperature: 230°C		
2.	Melt temperature: 250°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

